

## LMHC Information Sheet # 4

## Corundum

- Padparadscha sapphire definition
- Padparadscha sapphire report wording

Members of the Laboratory Manual Harmonisation Committee (LMHC) have standardised the nomenclature that they use to describe a 'padparadscha sapphire'.

## Definition

Padparadscha sapphire is a variety of corundum from any geographical origin whose colour is a subtle mixture of pinkish orange to orangey pink with pastel tones and low to medium saturation when viewed in standard daylight.

The name 'padparadscha sapphire' **shall not** be applied in the following cases:

- If the stone has any colour modifier other than pink or orange, even when induced by scattering effects on tiny inclusions (turbiditity)
- If the stone has major uneven colour distribution when viewed with the unaided eye and table up  $+/-30^{\circ}$
- The presence of yellow or orange epigenetic material in fissure(s) affecting the overall colour of the stone
- If the stone has been treated as described in Information Sheets #2 and #3
- If the stone has been treated by irradiation
- If the colour of the stone is not stable and shifting out of the padparadscha colour range (e.g. shifting to pink) by a colour stability test
- If the stone has been dyed, coated, painted, varnished or sputtered.

## **Report wording**

Any corundum that falls within the above definition shall be described as,

Identification:	
Species:	(natural) <sup>1</sup> corundum
Variety:	padparadscha (sapphire) <sup>1</sup>

Note: All terminology applied to corundum and set forth in Information Sheet #1 shall also be applied to 'padparadscha sapphire'. The name 'padparadscha sapphire' shall be applied to both unheated and heated 'padparadscha sapphire'.

In case the colour of a padparadscha is shifting during the colour stability test, but remains always within the padparadscha range: A sentence may be added in the comments section addressing this shifting property (e.g. mentioning: reversible photochromism and/or tenebrescence).

<sup>1</sup> wording in parenthesis is optional.

© 2023 Laboratory Manual Harmonisation Committee. This document may be freely copied and distributed as long as it is reproduced in its entirety, complete with this copyright statement. Any other reproduction, translation or abstracting is prohibited without the express written consent of the Laboratory Manual Harmonisation Committee.

All rights jointly reserved by:

Central Gem Laboratory CGL (Japan), CISGEM Laboratory (Italy), DSEF German Gem Lab (Germany), GIA Laboratory (USA), Gem and Jewelry Institute of Thailand GIT (Thailand), Gübelin Gem Lab Ltd. (Switzerland), Swiss Gemmological Institute - SSEF (Switzerland)